

JOINTING OF MORTAR BEDDED PAVING - CEMPOINT **(BS7533 parts 7&12)**

Q25 Slab / Brick / Sett & Cobble Paving

Clause 26a

This specification & method is fully compliant with BS7533 parts 7 & 12 for the grout jointing of paving elements. High performance grout is suited to medium to high traffic loads.

Material:

Ultrascape Cempoint – Gun injected mortar that’s pre-blended and delivered to site in moisture resistant bags.

Technical:

Ultrascape Cempoint can fill joint widths from 5mm – 25mm and depths up to 100mm and conforms to BS7533 parts 7 & 12. Ultrascape materials are all pre-blended and require only the simple addition of water on site. Always follow manufacturer’s instructions for mixing and application.

Preparation:

Joints must be free of any loose debris and clean.

Joints must be pre-soaked and remain wet until the jointing mortar is injected.

Grout Consistency:

Follow manufacturers recommendation for water content and mix for between 3 & 5 minutes until a smooth mix is achieved.

Application:

Transfer material into Cempoint gun using a trowel. Ensure a good contact with the substrate before moving steadily along prepared joints.

Finishing:

Material should be tooled off whilst still in its plastic form (wet).

Further Information:

Instarmac are happy to give advice and site support for specific projects.

Instarmac Group Plc Tel: +44(0) 1827 872244

www.instarmac.co.uk

email@instarmac.co.uk